

SPECIFICATION

Range: **SNOWKING**

Design: **(a+b) Dominoni, Quaquaro**

Description

Sistema modulare di sedute imbottite fonoassorbenti con struttura portante realizzata in materiale ligneo dimensionata in modo da assorbire autonomamente le basse frequenze e ricoperta con poliuretani e poliestere fonoassorbenti che, abbinati al rivestimento in tessuto fonoassorbente Snowsound Fiber 3 Melange e Fiber 6 Velvet realizzato con fibre di poliestere, consente alla seduta di assorbire al meglio le differenti frequenze. Il collegamento tra due o più sedute avviene nella parte superiore, mediante connettori in acciaio verniciato avvitati alla struttura degli schienali e posti tra gli schienali e i capitelli, nella parte inferiore il collegamento avviene mediante attacchi in metallo.

Meets the strength, durability and safety requirements of
EN 16139:2013+AC:2013 level 1


Results obtained in tests according to the standards:

EN 16139	prot.n. 332121-/333350-1/2022
EN 16139	prot.n. 332121-/333350-2/2022
EN 1728	prot.n. 332121-/333350-3/2022
EN 1728	prot.n. 332121-/333350-4/2022
EN 1728	prot.n. 332121-/333350-5/2022
EN 1728	prot.n. 332121-/333350-6/2022
EN 1728	prot.n. 332121-/333350-7/2022
EN 1728	prot.n. 332121-/333350-8/2022
EN 1728	prot.n. 332121-/333350-9/2022
EN 1022	prot.n. 332121-/333350-10/2022

FIRE REACTION CLASS

Seat fire reaction, Class 1IM according to UNI 9175 and UNI 9175/FA1

Dimensions:



Characteristics of the external fabric FIBER 3 MELANGE

Composition: acoustic fibers 100% polyester. No detectable formaldehyde contents.

Weight: 340 (g/m²) - 476 (g/linear meter)

REACTION TO FIRE

Italian Class : Class1. Test executed according to UNI 8456 and UNI 9174

Euroclass: B-s1, d0. Reaction to fire classification according to UNI EN 13501-1, executed following UNI EN ISO 11925-2 and UNI EN 13823

French Class : ClassM1. Test executed according to NF P 92-503 (1995) / NF P 92-504 (1995) and NF P 92-505 (1995)

Exyernal fabric is **Greenguard Gold certified**, validating its low VOC emission characteristics and its contribution to indoor environmental quality.

ABRASION RESISTANCE OF FABRICS - MARTINDALE MACHINE METHOD

50.000 rubs

Test executed according to UNI EN ISO 12947-2:2000

DETERMINATIONS OF FABRIC PROPENSITY TO SURFACE FUZZING AND TO PILLING

CLASS 5 (5.000 rubs)

Test executed according to UNI EN ISO 12945-2:2002

COLOUR FASTNESS TO ARTIFICIAL LIGHT: Xenon arc fading lamp test (BLUE SCALE)

FASTNESS INDEX: 7

Test executed according to UNI EN ISO 105-B02:2014

Characteristics of the external fabric FIBER 6 VELVET

Composition: acoustic fibers 100% polyester. No detectable formaldehyde contents.

Weight: 425 (g/m²) - 1275 (g/linear meter)

REACTION TO FIRE

Italian Class : Class1. Test executed according to UNI 8456 and UNI 9174

Euroclass: B-s1, d0. Reaction to fire classification according to UNI EN 13501-1, executed following UNI EN ISO 11925-2 and UNI EN 13823

French Class : ClassM1. Test executed according to NF P 92-503 (1995) / NF P 92-504 (1995) and NF P 92-505 (1995)

Exyernal fabric is **Greenguard Gold certified**, validating its low VOC emission characteristics and its contribution to indoor environmental quality.

ABRASION RESISTANCE OF FABRICS - MARTINDALE MACHINE METHOD

65.000 rubs

Test executed according to UNI EN ISO 12947-2:2000

DETERMINATIONS OF FABRIC PROPENSITY TO SURFACE FUZZING AND TO PILLING

CLASS 5 (5.000 rubs)

Test executed according to UNI EN ISO 12945-2:2002

COLOUR FASTNESS TO ARTIFICIAL LIGHT: Xenon arc fading lamp test (BLUE SCALE)

FASTNESS INDEX: 6/7


Test executed according to UNI EN ISO 105-B02:2014

ACOUSTIC PERFORMANCE

Measurement of sound absorption coefficient calculated according to ISO 354:2003, Frequency Hz / Aobj




cod. 7DDQ1-F6	125 Hz / Aobj 0,71 m ²
External textile cover	250 Hz / Aobj 1,09 m ²
Fiber 6 Velvet	500 Hz / Aobj 1,49 m ²
	1000 Hz / Aobj 1,67 m ²
	2000 Hz / Aobj 1,84 m ²
	4000 Hz / Aobj 2,08 m ²



cod. 7DDQ2-F6	125 Hz / Aobj 2,48 m ²
External textile cover	250 Hz / Aobj 2,49 m ²
Fiber 6 Velvet	500 Hz / Aobj 3,15 m ²
	1000 Hz / Aobj 3,58 m ²
	2000 Hz / Aobj 4,25 m ²
	4000 Hz / Aobj 4,97 m ²

Configuration examples




OPTIONAL

A+E Technology , Electromagnetic reduction

The sofa is arranged to accommodate a layer of RF-reducing fabric inside if requested.

Inner cover consisting of a layer of radio frequency reducing fabric made of technopolymer metallised with pure silver capable of reducing radio frequencies without completely obstructing signals so that smartphones and Wi-Fi networks can continue to be used. The radio-frequency reducing fabric is inserted into the seats between the frame and the upholstery, making it possible to combine the functions of acoustic reverberation reduction and radio-frequency reduction. A new patented technology designed for people's well-being.



Available colors “Melange”:



Available colors “Velvet”:



Caimi Brevetti S.p.A. reserves, by its unappealable judgment, the right to modify without prior notice the building materials, the technical and aesthetic specifications, as well as the dimensions of the products in this technical sheet, where pictures are purely as an indication.